

# Axton Walls&Windows or Cracks and gaps Acrylic Sealant white 280 ml – Variant 2

Revision: 29/08/2018

Page 1 from 2

## Technical data

Basis	Acrylic dispersion
Consistency	Paste
Curing system	Physical drying
Skin formation* (23°C/50% R.H.)	Ca. 20 min
Density**	Ca. 1,70 g/ml
Maximum allowed distortion	Ca. 12 %
Temperature resistance**	-20 °C → 80 °C
Application temperature	5 °C → 30 °C
Shrinkage	Ca. 15% (DIN 52451)

\* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. \*\* This information relates to fully cured product.

## Product description

S20-L2-W&W2-Acr is a one-component, quickly paintable, plasto-elastic sealant based upon acrylic dispersion. Due to its unique composition, it minimalizes the risk for crazing, even with highly filled and covering paints.

## Properties

- Very easy to apply
- Colourfast and waterproof after curing
- Can be painted over after curing
- Very good adhesion on many porous surfaces and aluminum

## Applications

- Joints with movement till max. 12,5%
- Connection joints in building industry.
- Joints on window sills, between plinths and walls, between masonry, ...

## Packaging

*Colour:* white, grey, brown, black  
*Packaging:* 310 ml cartridge, 600 ml sausage

## Shelf life

At least 12 months in unopened packaging in a dry storage place at temperatures between +5 °C and +25 °C. Protect against frost.

## Substrates

*Substrates:* all common porous building substrates

*Nature:* clean, free of dust and grease.

*Surface preparation:* Highly porous surfaces should be primed with diluted S20-L2-W&W2-Acr ( 1 part S20-L2-W&W2-Acr + 2 parts water).

Not suitable for natural stone, bitumen, glass and metal. We recommend a preliminary adhesion test on every surface.

## Joint dimensions

*Min. width for joints:* 5 mm

*Max. width for joints:* 20 mm

*Min. depth for joints:* 5 mm

Recommendation sealing jobs: joint width = joint depth. Use PE backer rods before applying the sealant in large joints to avoid 3-point adhesion.

## Application method

Do not apply when rain or frost is imminent during curing process.

*Application method:* With manual- or pneumatic caulking gun. Finish with a spatula or putty knife.

*Cleaning:* Before curing, S20-L2-W&W2-Acr can be removed with water from tiles and tools.

*Finishing:* Finish with a spatula or putty knife.

*Repair:* With the same material

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.